

Pool Equipment Pad Product Information



Test Description	Result	Test Method
Water Absorption	< 1.0%	ASTM D2842
Compressive Strength @ 5% strain @ 23°C	63.8 psi	ASTM D1621 & ASTM C165
Uniform load capacity of pool pad @ 23°C	>100,000 lbs.	-
Dimensional Stability: Thermal & Humid Aging	< 1.0%	ASTM D2126 ASTM C1622 & ASTM C303 & ASTM D3575
Density	80 kg/m ³ (5.0 pcf)	ASTM G21
Fungi Resistance	No fungal growth supported	